

Objet TangoBlackPlus FLX980 and TangoPlus FLX930

	ASTM	UNITS	METRIC	UNITS	IMPERIAL
Tensile Strength	D-412	MPa	0.8-1.5	Psi	115-220
Elongation at Break	D-412	%	170-220	%	170-220
Compressive Set	D-395	%	4-5	%	4-5
Shore Hardness (A)	D-2240	Scale A	26-28	Scale A	26-28
Tensile Tear Resistance	D-624	Kg/cm	2-4.	LB/in	18-22
Polymerized Density	ASTM D792	g/cm ³	1.12-1.13		

All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.



CONSULTING



3D-DESIGN



3D-PRINTING



MANUFACTURE

18 Rivulet Crescent
 Albion Park Rail, 2527, NSW, Australia.
 t. +61 2 4257 3201 f. +61 2 4257 3202
 e. support@tceg.com.au

CAMMPRO.COM.AU

THE CAMM ENGINEERING GROUP