

## Objet VeroWhitePlus RGD835 Objet TangoBlackPlus FLX980/TangoPlus FLX930

	ASTM	UNITS	RGD8505-DM, RGD8510-DM, RGD8515-DM, RGD8520-DM	RGD8526-DM, RGD8425-DM (Only Objet TangoPlus FLX930)
Tensile Strength	D-638-03	MPa	40-60	35-45
Elongation at Break	D-638-05	%	15-25	20-30
Modulus of Elasticity	D-638-04	MPa	1700-2300	1400-2000
Flexural Strength	D-790-03	MPa	55-75	45-60
Flexural Modulus	D-790-04	MPa	1500-2500	1400-1800
HDT, °C @ 0.45MPa	D-648-06	°C	40-45	40-43

All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.



CONSULTING



3D-DESIGN



3D-PRINTING



MANUFACTURE

18 Rivulet Crescent  
Albion Park Rail, 2527, NSW, Australia.  
t. +61 2 4257 3201 f. +61 2 4257 3202  
e. support@tceg.com.au

**CAMMPRO.COM.AU**

THE CAMM ENGINEERING GROUP