

Objet VeroWhitePlus RGD835 – Rigid, White Material

	ASTM	Metric	Imperial
Tensile Strength	D-638-03	55-60 MPa	7250-9450 psi
Modulus of Elasticity	D-638-04	2000-3000 MPa	290,000-435,000 psi
Elongation at Break	D-638-05	10-25 %	10-25 %
Flexural Strength	D-790-03	75-110 MPa	11000-16000 psi
Flexural Modulus	D-790-04	22000-32000 MPa	320,000-465,000 psi
Izod Notched Impact	D-256-06	20-30 J/m	0.375-0.562 ft. lb/in
HDT @ 0.45MPa	D-648-06	45-50 °C	113-122 °F
Water Absorption 24Hr	D570-98	1.1-1.5 %	1.1-1.5 %

All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.



CONSULTING



3D-DESIGN



3D-PRINTING



MANUFACTURE

18 Rivulet Crescent
Albion Park Rail, 2527, NSW, Australia.
t. +61 2 4257 3201 f. +61 2 4257 3202
e. support@tceg.com.au

CAMMPRO.COM.AU
THE CAMM ENGINEERING GROUP